

Client: TCS – The complete Service
57 Chancellors Road
Newry
N.Ireland
BT35 8PX

Entry No: 61368-01

Date received: 06/08/2013

Client's Description: Sample of fabric quality Douglas/UKS, ID 2525, Batch no. SA130715, Piece no. 37355, Audit TE1580

TEST REPORT

Test Required: Flammability in accordance with The Furniture and Furnishings (Fire) (Safety) Regulations 1988 and Amendments Schedule 4 Part I and Schedule 5 Part I

Pre-treatment: Water soaking in accordance with BS5651:1978 Clause 4 followed by Line drying

Conditioning: A minimum of 96 hours at 50 +/- 20% Relative Humidity, 20 +/- 5°C

Method of Test: BS 5852 : Part 1 : 1979

Date of Test: 12/08/2013

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Ignition Source	Observations	Result
0 (cigarette)	No flaming or progressive smouldering was observed within one hour of placement of the cigarettes.	PASS
1 (butane flame)	Flaming ceased within the specified two minute period after removal of the butane flame and no progressive smouldering occurred.	PASS

Note: 20-22 kg/m³ non fire retardant polyurethane foam was used as the filling.

Comments

On the basis of the tests carried out this sample of fabric meets the requirements of Schedule 4 Part I and Schedule 5 Part I.

-----End of Document-----

This is hereby certified to be a correct return of the tests made of the items referred to herein.




Geoff Briggs C.Text., A.T.I.
Head of laboratory
6th February 2014

- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days
- ❖ Test marked (*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
- ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- ❖ This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.

